

Technical Data Sheet



荣欣鑫橡胶助剂

RONGXIN XIN RUBBER ADDITIVES

E(E/C)-80

(E/C)-80		Pre-Dispersed Polymer Bound Chemicals
function		Vulcanizing agent
Description	composition	Mixture of 80% N - phenyl - N - (trichloromethyl - sulfonyl) - benzene sulfonic group acyl aniline and 20% polymer and dispersing agent
	Appearance	Off-white granules
	Density (g/cm ³)	Approximately 1.28
Application Notes		
Use	E - 80 adopts high purity superfine N - phenyl - N - (trichloromethyl - sulfonyl) - benzene sulfonic group acyl aniline with antistatic treatment, mixes with polymer and dispersant. E - 80 as rubber anti scorching agent, especially suitable for using with sulfonamide or thiazole accelerator, improve process safety and does not affect the physical properties, used for thiuram vulcanization system can only have mild or almost no anti scorching effect (but NBR mixture is an exception), if you add magnesium oxide, E - 80 has some anti scorching effect for NR/SBR thiuram vulcanization system. E - 80 will not produce contamination and discoloration	
Dosage	0.1 - 2 phr	
Packaging	25 kgs in carton box with polyethylene bag liner	
Storage	Keep cool (below 25℃) and dry in original package.24 months from production date	

Technical Data Sheet (TDS) Version 2.0

Henan Rongxin Technology Co.,Ltd.

TEL: 86-392-2632999 Email: sales@hrongxin.xin Web: www.hrongxin.xin